

Metadata of the chapter that will be visualized in SpringerLink

Book Title	NanoCarbon: A Wonder Material for Energy Applications	
Series Title		
Chapter Title	Carbon Nanomaterials as One of the Options for Hydrogen Storage	
Copyright Year	2024	
Copyright HolderName	The Author(s), under exclusive license to Springer Nature Singapore Pte Ltd.	
Corresponding Author	Family Name	Viswanathan
	Particle	
	Given Name	B.
	Prefix	
	Suffix	
	Role	
	Division	Department of Chemistry
	Organization	National Centre for Catalysis Research, Indian Institute of Technology
	Address	Madras, 600036, India
	Email	bviswanathan@gmail.com
Abstract	For the Hydrogen economy, cost-effective and safe storage of hydrogen assumes importance. Among the various modes of storage, solid-state storage has definite advantages for mobile and stationary applications. However, among the probable solid-state materials, the desired levels of storage (~6 Weight %) can be possible in carbon materials suitably modified with activation centers. A variety of modifications of carbon materials have been examined for hydrogen storage. However, the search has to continue till the desired levels of storage under ambient conditions are achieved.	
Keywords (separated by '-')	Hydrogen storage - Carbon nanomaterials - Graphene - Activation centers - Carbon allotropes - Solid-state storage	

Carbon Nanomaterials as One of the Options for Hydrogen Storage



B. Viswanathan

Abstract For the Hydrogen economy, cost-effective and safe storage of hydrogen assumes importance. Among the various modes of storage, solid-state storage has definite advantages for mobile and stationary applications. However, among the probable solid-state materials, the desired levels of storage (~6 Weight %) can be possible in carbon materials suitably modified with activation centers. A variety of modifications of carbon materials have been examined for hydrogen storage. However, the search has to continue till the desired levels of storage under ambient conditions are achieved.

Keywords Hydrogen storage · Carbon nanomaterials · Graphene · Activation centers · Carbon allotropes · Solid-state storage

1 Introduction

The energy needs of the world have been centered around carbon-based materials for a number of centuries. There are various forms of carbon materials that are available. It appears that the variety of carbon forms may be endless, and a simple classification is given in Table 1.

Five decades ago, a concept based on the Hydrogen Economy has been evolving and the transformation towards this economy essentially depends on the three components namely generation, storage, and delivery of hydrogen. There are consistent attempts to generate hydrogen from the decomposition of water from renewable sources) and this pursuit is an ongoing exercise to make this process economically feasible, though the desired level of success is still to be achieved. Commonly available methods for the storage of hydrogen, namely in high-pressure gas cylinders (up to 800 bar) and as liquid hydrogen in cryogenic tanks (at 21 K) are energy inefficient and not safe for certain applications, especially for mobile applications. Hydrogen

B. Viswanathan (✉)

Department of Chemistry, National Centre for Catalysis Research, Indian Institute of Technology, Madras 600036, India

e-mail: bviswanathan@gmail.com

© The Author(s), under exclusive license to Springer Nature Singapore Pte Ltd. 2024
R. K. Gupta (ed.), *NanoCarbon: A Wonder Material for Energy Applications*,
Engineering Materials, https://doi.org/10.1007/978-981-99-9935-4_15

1

Table 1 A classification scheme for carbon allotropes, molecular crystals, and derived forms

Sp^3	Sp^2	Sp^1
Diamond Cubic Hexagonal	Graphite Hexagonal Rhombohedral	Carbyne A-Carbyne B-Carbyne Chaoite
$Sp^3 + Sp^2 + Sp^1$	Sp^n ($3 < n > 1$, $n \neq 2$)	
Mixed forms of carbon	Intermediate forms of carbon	Intermediate forms of carbon
Amorphous carbon Glassy carbon Carbon black Adamantine carbon	$3 > n > 2$ Fullerene C_x $X = 60, 70, 84$ (When $x = \infty$, $n = 2$) Carbon onions Carbon nanotubes	$2 > n > 1$ Cyclo (N) carbons $N = 18, 24, 30$ (When $N = \infty$, $n = 1$)

25 adsorption/absorption on solid materials with high specific surface area and chem-
 26 ically bonded in covalent and ionic bonds appears to be attractive. Materials such
 27 as metal hydrides, alloys, complex hydrides, and high surface area porous materials
 28 are showing an affinity for ab(ad)sorbing large amounts of hydrogen. However, each
 29 of these storage materials suffers from some particular drawbacks. These materials
 30 crystallize in closed packed configurations giving rise to tetra-/octahedral- or other
 31 voids thus possibly restricting one hydrogen species per void space at room temper-
 32 ature and atmospheric pressure, which means the weight percent of storage capacity
 33 depends on the atomic or molecular weight of the nature of solid storage medium.
 34 In the solid-state hydrogen storage, hydrogen is bonded by either physical forces
 35 (Physical adsorption or van der Waals forces), e.g., MOF and carbon-based materi-
 36 als, or chemical forces (chemisorption involving chemical bonds), e.g., hydrides,
 37 imides, and nitrides. Physisorption has the advantages of higher energy efficiency
 38 and faster adsorption/desorption cycles, whereas chemisorption results in the adsorp-
 39 tion of larger amounts of gas but in some cases, is not reversible and requires higher
 40 temperatures to release the adsorbed gas which is not suitable for mobile applications.

41 The development of hydrogen storage materials with lightweight, high capacity,
 42 high stability, and better safety is imperative for portable electronics and transport
 43 applications. Carbon-based materials with different (allotropic) forms and chemical
 44 affinity are favorable for hydrogen storage application due to their low atomic weight,
 45 high surface area, porous nature, and higher safety characteristics. Carbon can be
 46 hybridized in Sp , Sp^2 , and Sp^3 bonds, and exist in 0D, 1D, 2D, and 3D forms. Addi-
 47 tionally, chemical and physical properties of these materials can be altered by using its
 48 different sources, composites, functional derivatives, or doping with other elements.
 49 It may possess pores of different shapes and sizes, which are ideal physisorption/
 50 ad(ab)sorption sites for hydrogen storage. In the following, the hydrogen storage
 51 capacities of different carbon nanostructures, including activated carbon, graphite,
 52 graphene, CNTs, fullerene, and CNFs, are discussed. The attempts to store on modi-
 53 fied (especially metal loaded) carbon materials also will be considered. Recent and

54 relevant efforts for improving the hydrogen storage capacities are also considered.
55 There are a variety of these materials and nature has shown that this is one of the
56 potential storage media for hydrogen (in the form of hydrocarbons) and also shown
57 that storage can go up to 25 weight percent (as in methane). However, one must be
58 aware these hydrocarbon molecules are covalent in nature and thus may not readily
59 release hydrogen when required as in transport applications. In this presentation, the
60 scope of carbon materials for hydrogen storage application is considered.

61 The microporosity of carbon materials is not directly related to hydrogen storage
62 application but a nearly linear relationship has been realized with respect to BET
63 surface area, typical plots can be seen in the following reference and references
64 cited therein [1]. There have been many attempts to modify the surface of carbon
65 materials so that the storage capacity can be increased. One such attempt deals
66 with the presence of heteroatoms on the surface of carbon materials for various
67 reasons like the possibility of dissociating molecular hydrogen or facilitating the
68 spill-over process. However, the current situation with respect to hydrogen storage
69 in carbon materials with heteroatoms can be stated that typically N-doping is only
70 apparent when considering the hydrogen uptake as a function of microporosity (rather
71 than total porosity). This possibly leads to the conclusion that pores larger than the
72 micropore size range have a lesser role in hydrogen storage capacity.

73 The advanced design and testing of carbon materials for energy storage devices
74 appear to be important. The main shortcomings of these materials are related to irre-
75 versible capacity loss, big voltage crosstalk, and low density [2]. Novel composites
76 containing multifunctional nanostructured carbon and other dopants can synergisti-
77 cally take advantage of the combination of ordered building block units with other
78 desired properties. Since most physisorption is involved in this process of hydrogen
79 storage, only a small amount of hydrogen could be stored even at a pressure of 90 bar.
80 Obviously, temperature (~room temperature) will have an almost negligible effect
81 on hydrogen storage capacity.

82 2 Activated Carbon

83 Activated carbon is one of the widespread and commercially used porous carbon
84 materials, consisting of graphite crystallites and amorphous carbon. It has been used
85 for centuries as an adsorbent due to its good adsorption capacity, high specific surface
86 area (up to ~3000 m²/g), porous structure, inertness, surface reactivity, and thermal
87 stability. The pores range from micro to macro size with an abundance of micro-
88 sized pores of <1 nm. Due to its widespread pores, it is a potential material for
89 hydrogen storage. In general, the hydrogen adsorption on such materials is propor-
90 tional to the specific surface area (SSA) and pore volume. Several research efforts are
91 devoted to finding the hydrogen uptake in activated carbon materials with different
92 pore sizes, pore volume, and specific surface area. Most of the experimental findings
93 have demonstrated the hydrogen storage capacity of activated carbon as 2.5 and 5.5
94 wt.% at low pressure (1–10 bar) and high pressure (up to 60 bar), respectively. It

95 was observed that at 100 bar and room temperature, the hydrogen uptake of acti-
 96 vated carbon was <1 wt.%, even with a highly porous structure and high specific
 97 surface area. It has been observed by different researchers that the optimum pore
 98 size in activated carbon for hydrogen storage is 0.6 nm. Table 2 shows the experi-
 99 mental results reported (compiled) of hydrogen storage capacity of activated carbons
 100 at different temperatures and pressure conditions. Different chemical treatments and
 101 doping of activated carbon were also utilized to improve the hydrogen uptake of acti-
 102 vated carbon materials. However, they do not meet the U.S. Department of Energy
 103 (DOE) target, and further efforts are needed to realize their potential for enhanced
 104 hydrogen storage capacity.

105 One can assess that the highest value of excess adsorption of hydrogen reported
 106 for a commercial activated carbon is around 5 wt.% at 77 K and pressures from 3 to
 107 6 MPa. In the case of activated carbons prepared on a laboratory scale, the best value
 108 obtained is ~7 wt.% at 77 K and 20 MPa. Most of the studies reported in the literature
 109 mainly concentrated on increasing the surface area of the activated carbon (by an
 110 appropriate method for (mostly chemical) activation) and the porosity of the material.
 111 The linear correlations connecting adsorption capacity and physical parameters like
 112 surface area and pore volume of activated carbons have been attempted but the results
 113 available indicate only limited applicability. It is also to be noted that activated
 114 carbons show hydrogen adsorption capacities at cryogenic conditions and this is not
 115 very suitable for the applications envisaged for hydrogen economy.

Table 2 Data on hydrogen storage capacities of different activated carbon materials (Data from literature)

Adsorbent employed	Reported hydrogen storage (wt.%)	Conditions (temperature and pressure)
Activated carbon	0.67	303 K 10 MPa
Activated carbon	1.4	77 K 0.1 MPa
Activated carbon	1.6	298 K 13 MPa
Activated carbon	4.5	77 K
Activated carbon	5.7	77 K 3 MPa
Activated carbon	3.2	298 K 20 MPa
Activated carbon	6/5	298 K 50 MPa
Chemically activated carbon	8.0	77 K 4 MPa
Activated carbon	2.3–5.8	77 K 4 MPa
Activated carbon (treated with KOH)	6.6	4 MPa
Activated carbon (activated with Ni)	1.8	77 K 0.1 MPa
Activated carbon (activated with Pt)	2.3	298 K 10 MPa
Activated carbon (activated with Pd)	5.5	298 K 8 MPa

3 Graphite

Graphite has Sp^2 hybridized carbon atoms arranged in a hexagonal lattice with a layered structure such that the layers themselves are held together by van der Waals forces of interaction. Graphite can be naturally obtained or can be artificially prepared. It is also widely explored for hydrogen storage applications. Various studies have modified their porosity, chemical bonding, and surface area by using different activation methods as well as doping them with different metals. Ball-milled graphite and intercalated graphite are widely explored for hydrogen storage applications. Ball-milled graphite contains tremendous defect sites and high surface area, which lead to chemisorption resulting in high hydrogen storage capacity. The ball-milling-induced rupture of graphite sheets and the emerging active edges and defects on the fragmented part are also confirmed by neutron scattering and spin resonance studies.

4 Graphene: The Hydrogen Adsorption/Desorption Isotherm

The hydrogen adsorption/desorption isotherm of the nitrogen-doped graphene, Graphitic Oxide and Graphite powder is shown in Ref. [3]. The hydrogen adsorption isotherm has been carried out at 298 K and 90 bar pressure. The nitrogen-doped graphene material showed nearly ~1.5 wt.% hydrogen storage capacity at room temperature and 90 bar pressure. In this context, the graphitic oxide (GO) showed ~0.21 wt.% hydrogen storage capacity at room temperature and 90 bar. This value is less than that of nitrogen-doped graphene material. However, nitrogen doping of graphene materials takes up substitution positions in the carbon lattice, there is transportation of hydrogen atoms on to the graphene surface. Furthermore, these results reveal that the nitrogen doping on graphene materials can extensively modify the catalytic effect of the graphene materials for hydrogen dissociative adsorption, foremost for the improvement of the dissociative hydrogen adsorption. This observation suggests that the nitrogen atoms possibly take part in a role in the hydrogen adsorption capacity at room temperature. A previous study recommended that the presence of nitrogen atoms in graphene sheets increases the enthalpy of hydrogen adsorption [4]. Potentially almost all the adsorbed amount can be desorbed which is an interesting characteristic expected for hydrogen storage materials. Various attempts have been made to modify or adopt different preparation procedures for graphene materials and it has been shown that N and P doping in graphene does not improve the materials' hydrogen storage capacity [5]. It has been proposed that the hydrogen binding energy can be tuned as a function of the graphene local curvature. The adsorption is facilitated by convex sites and desorption is facilitated on concave sites. The corrugation of graphene flakes and its control with large variety of functionalization may make these materials can impact in the search for hydrogen storage [6].

5 Modification of Activated Carbon

For conventional activated carbon materials, the hydrogen uptake is proportional to the surface area and pore volume; and normally the data are fitted well with the Langmuir isotherm model (monolayer adsorption). High adsorption capacity is only obtained at extremely low cryogenic temperatures and high pressures. Hydrogen adsorption on various types of commercial and modified activated carbon products has been extensively studied. Experimental results show that products with micropore volumes greater than 1 mL/g are able to store ca. 2.2 wt.% of hydrogen due to physisorption and it is expected that optimization of the adsorbent and sorption conditions could lead to a storage capacity of 4.5–5.3 wt.%. Agricultural waste materials such as coconut shells, coconut fibers, jute fibers, nut shells, oil seeds, etc., are popular raw materials for producing activated carbon materials. Carbon materials and their activation have been extensively discussed in Ref. [7]. Jin et al. [8] prepared activated carbons with different porosities using chemically activated coconut shells. They reported a maximum hydrogen adsorption capacity of 0.85 wt.% at 100 bar and 298 K. Sharon et al. [9], produced activated carbon fibers (ACF) using soybean and bagasse. The authors measured hydrogen storage capacities of 1.09–2.05 wt.% at a pressure of 11 Pa and room temperature. Another form of AC, the advanced AC monoliths, with good mechanical strength (maximum compression strength of 22 MPa), high volume of micropores (up to 1.04 cm³/g), and high density (up to 0.7 g/cm³) have been shown to adsorb 29.7 g/L of hydrogen at 77 K and 4 MPa [9]. Mechanically milled AC consists of some form of defective nanostructure, which increases the specific surface area. Research findings have revealed that after 10 h of milling, the hydrogen storage capacity increases from 0.90 wt.% to ca. 1.7 wt.%. Studies have shown that the loading of precious metals, e.g., Pt, onto AC, increases the adsorption capacity. The merging of the two adsorption phenomena, i.e. chemisorption (on the Pt surface) and physisorption (on the carbon surface) gives rise to a significant amount of spillover hydrogen.

6 Carbon Nanotubes

Ever since the discovery of carbon nanotubes was reported in 1991, there have been various attempts to use this new type of carbon material for hydrogen storage. These studies have led to some unexpected levels of storage up to nearly 60 wt.% or even more. However, the consensus now is that these reports claiming over 60 wt.% are flawed by experimental aberrations.

Only limited data are given in Table 3. For more extensive compilations, one is directed to references [35]. Various nanotubes like carbon nanotubes, boron nitride nanotubes, silicon carbide nanotubes, carbon nano-scrolls, pillared Graphene, and porous nanotube network materials have been extensively investigated and the final suggestion is that one should design novel materials with the following key

194 parameters namely high accessible surface area, large free pore volume and strong
195 interactions between the surface-active sites and the substrate hydrogen.

196 In a recent review, Lyu et al. [36] propose that “a detailed study of the optimum
197 number of metal atoms without aggregation on CNT should be performed. (1) At
198 the same time suitable preparation methods for realizing controllable doping sites
199 and doped configurations should be devised; (2) The material synthesis, purification,
200 and activation methods have to be optimized; (3) Active sites, molecular configura-
201 tions, effectively accessible surface area, pore size, surface topology, the chemical
202 composition of the surface, applied pressure and temperature, defects, and dopant,

Table 3 Selected data (for comparison) on the storage of hydrogen by carbon nanotubes

Sample	Temp (K)	P (MPa)	Hydrogen storage (wt.%)	Refs.
Herring bone GNFs	RT	11–35	67.5	[10]
Platelet GNFs	RT	11–35	53.68	[10]
Graphitic nano fibers	RT	101	10	[11]
Graphitic nano fibers	RT	8–120	10	[12]
SWNTs (low purity)	273	0.4	5–10	[13]
SWNTs (high purity)	80	70–80	8.25	[14]
SWNT (high purity + Ti alloy)	300–600	0.7	3.5–4.5	[15]
Li-MWNTs	473–673	1	20	[16]
Li-MWNTs (KOMWNTs)	473–673	1	2.5 (1.8)	[17]
MWNTs	RT	Ele-	<1	[18]
SWNTs	300–520	1–100	0.1	[19]
Various CN	RT	1	<0.1	[20]
SWNTs (+ Ti alloy)	RT	35	0	[21]
SWCNT	RT	0/8	4.5	[22]
SWCNT	295	10	0.93	[23]
SWCNT	RT	0.1	1.2	[24]
SWCNT	323	4.8	4.77	[25]
SWCNT	–	–	–0.8	[26]
MWCNT	–	3	2	[27]
MWCNT	77	0.005	0.54	[28]
MWCNT	298	0.1	0.2	[29]
NWCNT	425	10	3.8	[30]
MWCNT	143	3	3.5	[31]
MWCNT	RT	7.5	1.5–2.1	[32]
MWCNT	–	–	2.7–3.8	[31]
Carbon nano onion	77	1.5	>18.2	[33]
g-C ₃ N ₄ nanotubes	RT	37	0.78	[34]

203 which are some of the important factors that strongly affect the hydrogen absorption
204 in carbon nanotubes” should be elucidated.

205 In contrast, Lobo et al. [37], propose carbon nanostructures are promising materi-
206 als for hydrogen storage applications. They emphasize that hydrogen can be
207 physisorbed in carbon nanotube bundles on various sites such as external wall
208 surfaces, grooves, and interstitial channels. Therefore, it can have a large energy
209 density (as required for mobile applications). It is also known that by tuning the
210 adsorption conditions, hydrogen can be either chemisorbed or physisorbed in carbon
211 nanotubes. In a review, Lee et al. [38] and others [39] propose that a more detailed
212 understanding of the interfacial interactions between adsorbent and adsorbate should
213 be evolved and the phenomenon of spill-over can contribute to adsorbent surfaces to
214 achieve the desired levels of hydrogen storage.

215 **7 Impact of Structures on Hydrogen Storage in Different** 216 **Carbon Materials**

217 Increasing hydrogen storage to the levels advocated by DOE through materials in
218 the nanoscale has been proposed and intensively researched but the success appears
219 to elude us. Among the several options available, various allotropic forms of carbon,
220 like CNTs, graphene, and activated carbons have been considered to be appropriate
221 systems owing to their unique properties like high surface area, (this parameter has
222 limited linear variation with absorbed hydrogen) porous nature (but pore volume is
223 limited for each material) and high thermal and mechanical stability, and all these
224 have been so far considered though questionable? As vital factors for hydrogen
225 storage. Emphasis has been given to the hollow and porous structure of CNTs which
226 is supposed to give the possibility of hydrogen storage both in the inner and outer
227 surfaces that are well investigated by many theoretical as well as experimental studies.
228 These studies though have relevance did not answer the stumbling block in achieving
229 the goal of reaching the DOE standards. CNTs are termed to be one of the promising
230 nanostructures for hydrogen storage however this expectation also has not yielded
231 the desired result.

232 Moreover, the simultaneous presence of defects, both topological and structural
233 types, and other irregularities affect the activation and adsorption and hence the
234 amount of hydrogen stored in the system. In addition to this, doping also leads to
235 structural and electronic property variations. However, these modifications so far
236 have not shown enormous improvement in hydrogen storage capacity. It is however
237 believed that estimated values of hydrogen storage still show the high impact of
238 structure on the storage capacity. Nanomaterials are also analyzed and found that
239 some of these strongly affect the storage capacity. But still, the DOE target could not
240 be achieved which makes this issue an interesting topic of study even today.

241 Different types of nanotubes like metallic and semiconductor (also single or multi-
242 walled) with varying structures were considered. It has been observed that the adsorp-
243 tion binding energy values as a function of different orientations of adsorbed species
244 and at different sites of nanostructures are compared and the results show the strong
245 impact of CNT structure on the storage capacity of hydrogen. Hydrogen can be
246 adsorbed on graphene in two different ways: physisorption or chemisorption. While
247 the first one is due to Van Der Waals interaction, the second is by forming a chemical
248 bond with the C atoms. Physisorption usually happens with hydrogen in molecular
249 form and in chemisorption, dissociation of H₂ into atomic hydrogen takes place and is
250 a rather favorable process unlike in CNTs where physisorption is the most preferred
251 way of storage. A single graphene layer is a quasi-2D system, and its VD is not well
252 defined, thus in the evaluation of the potentialities of graphene for hydrogen storage,
253 different forms of graphene such as multilayers, three-dimensional assemblies, or
254 nanostructures of graphene are considered. However, it should be remarked that the
255 standards for the necessary hydrogen storage for the projected applications should
256 be realized at the earliest.

257 8 Modified Carbon Materials for Hydrogen Storage

258 Modification of the equipotential surface of carbon materials has been attempted
259 for various reasons. Usually, the activation is aimed at introducing active centers on
260 supported phases. It is usually to disperse active metals so that the exposed metal
261 surface area is maximum. Hydrogen adsorption involves dissociation of molecular
262 hydrogen and any storage medium should have dissociating centers for molecular
263 hydrogen. Recognizing this aspect, heteroatom substitution has been proposed as one
264 of the options. DFT calculations have also shown that molecular hydrogen dissocia-
265 tion energy is considerably reduced on heteroatoms like N, P, or B substituted carbon
266 surfaces (Table 5), however, these studies so far have not led to the levels of storage
267 of hydrogen on these materials.

268 8.1 Nitrogen Doping in Carbon Materials

269 Nitrogen is an abundant (80%) element in the terrestrial atmosphere. Molecular
270 nitrogen is stable and has a minor role in the lower atmosphere. N-doped carbon
271 materials are the much-studied area in energy storage. Depending on the type of
272 N bonding within the carbon matrix, nitrogen can share one to two π -electrons
273 with the π -electron system of the carbons. This sharing of electrons causes an n -
274 type doping if N atoms directly substitute the C atoms in the graphitic lattice. N-
275 doping in carbon generally manifests itself in three different forms namely, pyrrolic-
276 N, pyridinic-N, and quaternary-N, and each form alters the carbon electronic band

277 gap differently. The band gaps of pyrrolic-N, pyridinic-N, and quaternary-N-doped
 278 carbons are reported to be 1.20, 1.40, and 1.39 eV, respectively (Table 4).

279 Particularly, all materials obtained by these techniques have a nitrogen content
 280 lower than 10 atoms % because of the high temperature environment that was used
 281 in carbonization. An alternate synthesis method needs to be developed that enables
 282 the preparation of carbon material with high nitrogen content and time they should
 283 be stable at high temperatures. It will be beneficial if one can adopt a polymerization
 284 and low-temperature growth process to create nitrogen-doped carbon materials.

285 Nitrogen is essentially introduced into the carbon matrix in two ways, either
 286 by the carbonization of N-containing precursors or by post-modification methods.
 287 The common nitrogen-containing precursors are urea, melamine, cyanide, polyacry-
 288 lonitrile, and ammonia. Another resourceful approach for the synthesis of N-doped
 289 carbon materials is based on naturally (sustainable) nitrogen-containing precursors

Table 4 Bond length and dissociation energy of hydrogen on the CNTs calculated using B3LYP with 6.31G (P,D) basis set on the UFF optimized structures [40]

Substitution	Total energy (Hartrees)	Bond length H ₁ -H ₂ (Å)	Dissociation energy (eV)
Hydrogen	-1.175	0.708	4.76
CNT	-3686.5502
CNT + H ₂	-3687.7161	0.776	4/51
NCNT	-3702.5908
NCNT + H ₂	-3703.5989	0.815	0.22
PCNT	-3989.1694
PCNT + H ₂	-3990.2550	0/815	2.33
SCNT	-4046.0020
SCNT + H ₂	-3047.0067	0.817	0.13
BCNT	-3671.7254
BCNT + H ₂	-3672.9440	0.818	5.95
2BCNT (adjacent)	-3658.6666
2BCNT (adjacent) + H ₂	-3659.8092	0.813	3.88
2BCNT (Alternate)	-3659.3491
2BCNT (alternate) + H ₂	-3660.3594	0.928	0.28

Table 5 Technical system targets for on-board hydrogen storage for light-duty fuel cell vehicles

	2020	2025	Ultimate
Usable specific energy from H ₂ [kWh/kg]	1.5	1.8	2.2
Net usable energy/mass system mass [kg H ₂ /kg system]	0.045	0.055	0.065
Usable energy density from H ₂ [kWh/L]	1.0	1.3	1.7
Net usable energy/max system volume [kgH ₂ /L system]	0.030	0.040	0.050
System cost [USD/kWh net]	10	9	8

290 like amino-carbohydrates or other N-enriched polymers, amino acids, proteins, N-
291 ionic liquids, and waste crab shells. Another possible way is to pyrolyze the nitrogen
292 and carbon-containing precursors, such as heterocycles or melamine, by which direct
293 incorporation of nitrogen atoms into the forming of carbon backbone becomes
294 possible. One of the procedures for deriving N-doped carbon is hydrothermal
295 treatment of carbohydrate-rich biomass. Using nitrogen-containing biomass-related
296 precursors and hydrothermally treating them yields nitrogen-containing carbona-
297 ceous materials that offer tremendous possibilities for further treatments and energy
298 applications. The application of nitrogen-doped carbon materials has been investi-
299 gated as a material for hydrogen storage at room temperature and ambient pressure
300 [41]. It has been reported that nitrogen-enriched graphitic carbon material exhibits
301 a hydrogen storage capacity of 0.34 wt.% at 298 K under 100 bars [42]. It has also
302 been reported that the addition of N-species in mesoporous carbons showed hydrogen
303 adsorption capacity of 1.1 wt.% at 298 K and 100 bar pressure [43]. It has also been
304 reported that the microwave plasma CVD process enables the growth of specific
305 nanostructured nitrogen-doped carbons. Nitrogen incorporation into these forms of
306 carbon is approximately 1 at.%. It shows a gravimetric hydrogen storage capacity of
307 0.7–0.8 wt.% under 300 K and 0.1–7 MPa [44]. Hydrogen adsorption on nitrogen-
308 doped carbon xerogels showed maximum hydrogen uptake of 0.28 wt.% at 308 K
309 [45].

310 8.2 Phosphorus-Doping in Carbon Materials

311 The changes in the physical properties of Sp^2 carbon motifs after the addition of
312 phosphorous into their lattice are considered. However, P has a larger atomic radius
313 and higher electron-donating ability, which makes it an option as a dopant. Phos-
314 phorus is not a common element in carbons, although it is present in carbons obtained
315 using phosphoric acid activation. Due to the addition of P in the carbon matrix, the
316 density of states near the Fermi level is also found to increase, which increases with
317 the increase in the P-doping level. In these reactions, the formation of phosphate
318 and polyphosphate bridges provokes the expansion and cross-linking of the carbon
319 matrix, driving to an accessible pore structure after the removal of the acid. The
320 chemical state of phosphorus in carbons is a rather controversial issue. Some exper-
321 imental evidence using different analytical techniques (FTIR and XPS) has shown
322 that the most abundant P species introduced in carbons by phosphoric acid activa-
323 tion are $-C-P-$ or $-C-O-P$ bonds in phosphate and phosphonate-like structures. The
324 XPS analysis further allowed for an insight into the binding states, proving the true
325 incorporation of the phosphorus atoms into the graphite sheets, besides some P-O
326 binding sites, most likely on the surface of the material. The existence of pentava-
327 lent phosphorus and elemental phosphorus is very infrequently detected, except when
328 high temperatures are applied. Recent studies have reported that P-containing groups
329 might be significant for the progress of graphitic crystallites which contrasts with far
330 reported role of P as an inhibitor of carbon graphitization. Yang et al. [46] reported that

331 phosphorus-doped ordered mesoporous carbon was synthesized by co-pyrolyzing a
332 phosphorus-containing source and a carbon source collectively using ordered meso-
333 porous silica (SBA-15) as a template without the use of any metal components. More
334 recent approaches have recognized dissimilar synthetic pathways in the direction of
335 phosphorus-doped carbon materials, proving themselves as promising candidates for
336 energy storage applications. It has been shown in the previous section that carbon
337 materials with substitution by heteroatoms like N, S, and B, show hydrogen sorption
338 capacity. However, the effect of substitution of phosphorus in carbon materials has
339 not been investigated to the same extent.

340 **8.3 Boron-Doping in Carbon Materials**

341 Boron is an element with unique properties. It is thus an interesting candidate
342 for doping of carbon materials, modifying the properties of pure carbons. Several
343 researchers have started focusing not only on basic studies on B-doping, but also on
344 applying the obtained materials and exploiting their favorable properties in energy-
345 related applications. Due to its three valence electrons, B is well thought-out as a
346 good dopant. Substitutional boron enhances the graphitization of carbon. It has been
347 found that boron atoms are favored to be substituted in the graphite lattice. The
348 existence of B–C bonds in the carbon framework can lower the Fermi level of the
349 structure and then tune the properties of oxygen chemisorption and electrochemical
350 redox reactions. The synthetic procedure, in which elemental B and graphite powder
351 served as precursors, yielded a mixture of different B-containing carbon nanostruc-
352 tures, such as thin graphitic sheets, tubes, and filaments. The substitutional doping
353 of carbon atoms in Sp^2 and Sp^3 configurations with boron can modify the elec-
354 tronic and structural properties of the resulting carbon. Over the years boron-doped
355 carbons have been synthesized by standard CVD process using BCl_3 . Substituted
356 boron atoms in the carbon lattice accelerate the graphitization and suppress the
357 oxidation of carbon materials, which seems promising for their use as reinforce-
358 ment materials in aerospace applications. The positive effect of boron doping on
359 diamond and carbon electrodes and in the field of hydrogen storage has also been
360 reported, although further optimization of the boron doping environment seems yet
361 to be needed.

362 The storage of hydrogen in carbon nanomaterials requires appropriate chemical
363 activators in suitable geometry. Sankaran et al. reported different types of carbon
364 materials employed for the hydrogen sorption capacity. The storage capacity of
365 2 wt.% at 298 K and 80 bar pressure is obtained for boron boron-substituted carbon
366 nanotube. However, a maximum storage capacity of 2 wt.% is attained at 80 bar
367 and 300 K for boron-containing carbon nanotubes (BCNT) whereas pure carbon
368 nanotubes (CNT) show only 0.6 wt.% at 300 K and 80 bar and B-doped bulk
369 carbon material (PBC) shows only 0.2 wt.%. Mike Chung et al., reported the microp-
370 orous boron-substituted carbon (B/C) materials show a significantly higher hydrogen
371 binding energy and reversible hydrogen physisorption capacity of 0.6 and 3.2 wt.%

372 at 293 and 77 K, under 40 bar of hydrogen pressure [47]. B-containing polymeric
373 precursors and pyrolysis were employed to synthesize microporous B/C materials
374 with a high B content (7.2%) and high surface area (780 m²/g). The substitutional
375 B elements in B/C material serve as internal p-type dopants and polarize the C
376 surface, which exhibits a significantly higher hydrogen binding energy [48]. For
377 efficient hydrogenation and hydrogen storage, these boron atoms should be incor-
378 porated geometrically and chemically into the carbon network. Wang et al. reported
379 that B- and N-doped microporous carbon had a hydrogen storage capacity of 0.55
380 wt.% at 298 K and 10 MPa. By doping 6.0 wt.% Ru metal on the B- and N-doped
381 microporous carbon, the hydrogen uptake at 10 MPa was increased to 1.2 wt.%, i.e.
382 The improvement of hydrogen storage was due to the spillover of atomic hydrogen
383 from the Ru metal particles to the B-and N-doped microporous carbon [49].

384 9 Perspectives

385 The standards that one wishes to achieve in the storage of hydrogen are: [54–56].

- 386 • Gravimetric H density in the range of 5–10 wt.% H₂, and energy density of 1.6–3.2
387 kWh/kg.
- 388 • Volumetric H density >50 kg H₂ m⁻³ and energy density >1.6kWh/L.
- 389 • Thermodynamics: T 0 < 85 °C (transport applications) or <200 °C (stationary
390 applications).
- 391 • Kinetics (tank level): fill time 3–5 min; H₂ release flow 1.6 g/s.
- 392 • Durability: 1500 cycles (1/4 tank to full).

393 One of the recent specifications and the time to achieve them are assembled in
394 Table 5.

395 Of all the available hydrogen storage materials, why carbon materials are preferred
396 option? What is the maximum hydrogen storage capacity that can be expected and
397 what will be the limit that can be practically achieved? It may be remembered that
398 nature mostly provides hydrogen source in combined form with carbon and oxygen
399 though other elemental compositions are also possible. If carbon materials can be
400 obtained in an atomic state, then the maximum storage capacity can be expected to
401 be around 25 wt.%. However, since it is not possible to get atomic hydrogen, the
402 carbon materials can be obtained at the limit with one vacant valency in carbon two-
403 dimensional material and the maximum storage can be expected to be 6.25 wt.%.
404 This limit is arrived at assuming that hydrogen is held by the solid by valence forces.
405 If hydrogen is stored or retained by other forces, this limit may not hold good.

406 If the stored hydrogen were to occupy the interstitial sites in carbon materials,
407 then the energetics of storing and releasing should also be considered for practical
408 application.

409 Since normally carbon materials are microporous in nature, hydrogen may be held
410 in these pores by condensation forces and hence one can hope for higher storage

411 capacity, however, the experimental variables for this process namely temperature
412 and pressure have to be different from normal ambient conditions.

413 10 Conclusion

414 Hydrogen storage characteristics and treatments for improving the storage capacities
415 of different carbon materials are presented. The following deductions can be stated:

- 416 1. The hydrogen storage capacity of carbon materials depends upon surface area,
417 which is affected by micropore size distribution that counts for the presence of
418 narrow micropores.
- 419 2. Thermal treatments and metal doping on carbon nanostructures are observed to
420 be useful for improving hydrogen storage capacities but higher storage capacities
421 can be obtained at cryogenic temperature and higher pressure. Further investiga-
422 tions on modified carbon nanostructures may be useful to achieve the target of
423 7.5 wt.% for automobile applications.
- 424 3. Theoretical studies show a strong structural dependence of carbon materials on
425 hydrogen adsorption capacity, especially in CNTs. The defects influence the
426 adsorption capacity.
- 427 4. Several theoretical studies predicted amazing storage capacities but were not
428 confirmed experimentally. Also, higher storage capacities like 20 wt.% for metal
429 doped MWCNT and 10 wt.% for CNF measured experimentally are reported in
430 the literature but are to be confirmed.
- 431 5. Experimental and theoretical studies on adsorption storage reactors are scarce
432 in the literature. Studies on the design, material, and thermophysical properties
433 of reactors can be done for isotherm measurements, especially for automotive
434 applications. These vital issues will be a good technical contribution in the field
435 of hydrogen-adsorption systems for onboard applications.

436 Spill-over is one of the phenomena invoked by the transport of hydrogen from the
437 site of impact to other normally inactive sites. This phenomenon has been investigated
438 and is commonly accepted alternate way of surface transport. This transport requires a
439 transporting medium and in the case of hydrogen, it is usually water and its fragments.
440 In the case of carbon, this transporting medium can be either adsorbed water species
441 or the carbon species themselves. The role of spillover in hydrogen sorption and
442 storage needs more information.

443 References

- 444 1. Panella, B., Hirscher, M., Roth, S.: Hydrogen adsorption in different carbon nanostructures.
445 Carbon **43**, 2209 (2005)
- 446 2. Zhu, Z.H., Hatori, H., Wang, S.B., Lu, G.Q.: New insights into the interaction of hydrogen
447 atoms with boron substituted carbon. J. Phys. Chem. B **109**, 16744 (2005)

- 448 3. Arjunan, A., Viswanathan, B., Nandhakumar, V.: Nitrogen doped graphene as potential material
449 for hydrogen storage. *Graphene* **6**, 41 (2017)
- 450 4. Wang, L., Lee, K., Sun, Y.-Y., Lucking, M., Chen, Z., Zhao, J.J., Zhang, S.B.: Graphene oxide
451 as an ideal substrate for hydrogen storage. *ACS Nano* **3**, 2995 (2009)
- 452 5. Ariharan, A., Viswanathan, B., Nandhakumar, V.: Heteroatom doped multi-layered graphene
453 material for hydrogen storage application. *Graphene* **5**, 39 (2016)
- 454 6. Tozzini, V., Pellegrini, V.: Prospects for hydrogen storage in Graphene. *Phys. Chem. Chem.*
455 *Phys.* **15**, 80 (2013)
- 456 7. Viswanathan, B., Indraneel, P., Varadarajan, T.K.: A process for the preparation of activated
457 carbon from botanical sources. *Catal. Surv. Asia* **13**, 164 (2008)
- 458 8. Jin, H., Lee, Y.S., Hong, I.: Hydrogen adsorption characteristics of activated carbon. *Catal.*
459 *Today* **120**, 399 (2007)
- 460 9. Jorda-Beneyto, M., Lozano-Castello, D., Suarez-Garcia, F., Cazorla-Amoros, D., Linares-
461 Solano, A.: Advanced activated carbon monoliths and activated carbons for hydrogen storage.
462 *Microporous Mesoporous Mater.* **112**, 235 (2008)
- 463 10. Chambers, A., Park, C., Baker, R.T.K., Rodriguez, N.M.: Computer simulations of hydrogen
464 adsorption on graphite nanofibers. *J. Phys. Chem. B* **102**, 4253 (1998)
- 465 11. Fan, Y.Y., Liao, B., Liu, M., Wei, Y.L., Lu, M.Q., Chang, H.M.: Hydrogen uptake in vapor
466 grown carbon nanofibers. *Carbon* **37**, 1649 (1999)
- 467 12. Gupta, B.K., Srivastava, O.N.: Synthesis and hydrogenation behaviour of graphitic nanofibers.
468 *Int. J. Int. J. Hydrog. Energy* **25**, 825 (2000)
- 469 13. Dillon, A.C., Jones, K.H., Bekkedahl, T.A., Klang, C.H., Bethune, D.S., Eben, H.J.: Storage
470 of hydrogen in single-walled carbon nanotubes. *Nature* **386**, 377 (1997)
- 471 14. Ye, Y., Ahvi, C.C., Witham, C., Fultz, B., Liu, J., Rinzler, A.G., Colbert, D., Smith, K.A.,
472 Smalley, R.E.: Hydrogen adsorption and cohesive energy of single-walled carbon nanotubes.
473 *Appl. Phys. Lett.* **74**, 2307 (1999)
- 474 15. Dillon, A.C., Genneth, T., Jones, K.M., Alleman, J.A., Parilla, P.A., Heben, H.J.: A simple and
475 complete purification of single-walled carbon nanotube (SWNT) materials. *Adv. Mater.* **11**,
476 1354 (1999)
- 477 16. Chen, P., Wu, A., Lim, J., Tan, K.L.: High H₂ uptake by alkali doped carbon nanotubes under
478 ambient pressure and moderate temperatures. *Science* **265**, 91 (1999)
- 479 17. Yang, R.T.: Hydrogen storage by alkali-doped carbon nanotubes-revisited. *Carbon* **38**, 623
480 (2000)
- 481 18. Elzbeta Fracko Wiak and Francois Bequin: Electrochemical storage of energy in carbon
482 nanotubes and nanostructured carbons. *Carbon* **40**, 1775 (2002)
- 483 19. Hirscher, M., Bechner, M., Haluska, M., Quintel, A., Skakalova, V., Choi, Y.-M., Dettlaff-
484 Weglikowska, U., Roth, S., Stepanek, I., Bernier, P., Leonhardt, A., Fink, J.: Hydrogen storage
485 in carbon nanostructures. *J. Alloy. Compd.* **330–332**, 654 (2002)
- 486 20. Tiribetti, G.G., Heisner, G.P., Olk, C.H.: Hydrogen storage capacity of carbon nanotubes,
487 filaments, and vapor-grown fibers. *Carbon* **39**, 2291 (2001)
- 488 21. Hirscher, M., Becher, M., Haluska, M., Dettlaff-Weglikowska, U., Quintel, A., Duesberg, G.S.,
489 Choi, Y.M., Downes, P., Hulman, M., Roth, S., Stepanek, I.: Hydrogen storage in sonicated
490 carbon materials. *Appl Phys A* **72**, 129 (2001)
- 491 22. Chambers, A., Park, C., Baker, R.T.K., Rodriguez, N.M.: Hydrogen storage in graphite
492 nanofibers. *J. Phys. Chem. B* **102**(22), 4253–4256 (1998)
- 493 23. Nishimiya, N., Ishigaki, K., Takikawa, H., Ikeda, M., Hibi, Y., Sakakibara, T., Matsumoto, A.,
494 Tsutsumi, K.: Hydrogen sorption by single-walled carbon nanotubes prepared by a torch arc
495 method. *J. Alloy. Compd.* **339**, 275–282 (2002)
- 496 24. Smith, M.R., Bittner, E.W., Shi, W., Johnson, J.K., Bockrath, B.C.: Chemical activation of
497 single-walled carbon nanotubes for hydrogen adsorption. *J. Phys. Chem. B* **107**, 3752–3760
498 (2003)
- 499 25. Silambasaran, D., Surya, V.J., Vasu, V., Iyakutti, K.: Experimental investigation of Hydrogen
500 storage in single walled carbon nanotubes functionalized with borane. *Int. J. Hydrog. Energy*
501 **36**, 3574–3579 (2011)

- Author Proof
- 502 26. Rashidi, A.M., Nouralishahi, A., Khodadadi, A.A., Mortazavi, Y., Karimi, A., Kashefi, K.:
503 Modification of single wall carbon nanotubes (SWNT) for hydrogen storage. *Int. Hydrog.*
504 *Energy* **35**, 9489–9495 (2010)
- 505 27. Mosquera, E., Diaz-Droguett, D.E., Carvajal, N., Roble, M., Morel, M., Espinoza, R.: Charac-
506 terization and hydrogen storage in multi-walled carbon nanotubes grown by aerosol assisted
507 CVD method. *Diam. Relat. Mater.* **43**, 66–71 (2014)
- 508 28. Lee, S., Park, S.: Influence of the pore size in multi-walled carbon nanotubes on the hydrogen
509 storage behaviors. *J. Solid-State Chem.* **194**, 307–312 (2012)
- 510 29. Barghi, S.H., Tsotsis, T.T., Sahimi, M.: Chemisorption, physisorption and hysteresis during
511 hydrogen storage in carbon nanotubes. *Int. J. Hydrog. Energy* **39**, 1390–1397 (2014)
- 512 30. Lin, K., Mai, Y., Li, S., Shu, C., Wang, C.: Characterization and hydrogen storage of surface
513 modified multiwalled carbon nanotubes for fuel cell application. *J. Nanomater.* 1–12 (2012)
- 514 31. Rakhi, R.B., Sethupathi, K., Ramaprabhu, S.: Synthesis and hydrogen storage properties of
515 carbon nanotubes. *Int. J. Hydrog. Energy* **33**, 381–386 (2008)
- 516 32. Rostami, S., Pour, A.N., Izadyar, M.: A review on modified carbon materials as promising
517 agents for hydrogen storage. *Sci. Prog.* **101**, 171 (2018)
- 518 33. Sahu, S., Khan, M.S., Gupta, N., Chennakesavulu, K., Sasikumar, C.: The hydrogen storage
519 capacity of carbon nano-onions fabricated by thermal chemical vapour. *Int. J. Hydrog. Energy*
520 **48** (2023). <https://doi.org/10.1016/j.ijhydene.2023.03.156>
- 521 34. Guo, R., Teng, Y.-S., Retita, I., BakmanrokJ, G., Arhurst, N., Chan, S.L.I.: A detailed exper-
522 imental comparison on the hydrogen storage ability of different forms of graphitic carbon
523 nitride bulk, nanotubes and sheets with multiwalled carbon nanotubes. *Mater. Today Chem.*
524 **30**, 101508 (2023)
- 525 35. Lyu, J., Kudiiarov, V., Lider, A.: An overview of the recent progress in modifications of carbon
526 nanotubes for hydrogen adsorption. *Nanomaterials*, **10**, 255 (2020)
- 527 36. Lyu, J., Kudiiarov, V., Lider, A.: An overview of the recent progress in modifications of carbon
528 nanotubes for hydrogen adsorption. *Nanomaterials* **10**, 255 (2020)
- 529 37. Lobo, R., Ribeiro, J., Inok, F.: Hydrogen uptake and release in carbon nanotube electrocatalysts.
530 *Nanomaterials* **11**, 97 (2021)
- 531 38. Lee, S.Y., Lee, J.H., Kim, Y.H., Kim, J.W., Lee, K.J., Park, S.J.: Recent progress using solid-state
532 materials for hydrogen storage: a short review. *Processes* **10**, 304 (2022)
- 533 39. Lim, K.L., Kazemian, H., Yaakob, Z., Daud, W.W.: Solid-state materials and methods for
534 hydrogen storage: a critical review. *Chem. Eng. Technol.* **33**(2), 213–226 (2010)
- 535 40. Sankaran, M.: On the potential of carbon materials for solid state hydrogen storage. Ph.D.
536 thesis, IIT Madras (2007)
- 537 41. Yao, Y., Zhang, B., Shi, J., Yang, Q.: Preparation of Nitrogen-doped carbon nanotubes with
538 different morphologies from melamine-formaldehyde resin. *ACS Appl. Mater. Interfaces* **7**,
539 7413–7420 (2015)
- 540 42. Yang, S.J., Cho, J.H., Oh, G.H., Nahm, K.S., Park, C.R.: Easy synthesis of highly nitrogen
541 enriched graphitic carbon with high hydrogen storage capacity at room temperature. *Carbon* **47**,
542 1585–1591 (2009)
- 543 43. Cai, J., Bennici, S., Shen, J., Auroux, A.: The acid-base properties of nitrogen-containing carbon
544 materials. *Mater. Chem. Phys.* **161**, 142–152 (2015)
- 545 44. Badzian, A., Badzian, T., Breval, E., Piotrowski, A.: Nanostructured, nitrogen-doped carbon
546 materials for hydrogen storage. *Thin Solid Films* **398**, 170–174 (2001)
- 547 45. Kang, K.Y., Lee, B.I., Lee, J.S.: Hydrogen adsorption on nitrogen-doped carbon xerogels.
548 *Carbon* **47**, 1171–1180 (2009)
- 549 46. Yang, D.-S., Bhattacharjya, D., Song, M.Y., Yu, J.-S.: High efficient metal-free phosphorus-
550 doped platelet ordered mesoporous carbon for electrocatalytic oxygen reduction. *Carbon* **67**,
551 736–743 (2014)
- 552 47. Chung, T.M., Jeong, Y., Chen, Q., Kleinhammes, A., Wu, Y.: Synthesis of microporous boron-
553 substituted carbon (B/C) materials using polymeric precursors for hydrogen physisorption. *J.*
554 *Am. Chem. Soc.* **130**, 6668–6669 (2018)

- 555 48. Chung, T.M., Jeong, Y., Kleinhammes, A., Wu, Y.: Synthesis of micro-porous boron substituted
556 carbon (BC) materials using polymeric precursors for hydrogen physisorption. ECS Trans. **19**,
557 57–66 (2009)
- 558 49. Wang, L., Yang, F.H., Yang, R.T.: Hydrogen storage properties of B- and N-doped microporous
559 carbon. AICHE J. **55**, 1823–1833 (2009)

UNCORRECTED PROOF

Author Queries

Chapter 15

Query Refs.	Details Required	Author's response
AQ1	Please check and confirm if the author names and initials are correct.	
AQ2	Please be aware that your name and affiliation and if applicable those of your co-author(s) will be published as presented in this proof. If you want to make any changes, please correct the details now. Please note that after publication corrections won't be possible. Due to data protection we standardly publish professional email addresses, but not private ones, even if they have been provided in the manuscript and are visible in this proof. If you or your co-author(s) have a different preference regarding the publication of your mail address(s) please indicate this clearly. If no changes are required for your name(s) and affiliation(s) and if you agree with the handling of email addresses, please respond with "Ok".	
AQ3	Please check and confirm if the inserted citation of Table 4 is correct. If not, please suggest an alternate citation. Please note that tables should be cited sequentially in the text.	
AQ4	References [54–56] are cited in the text but not provided in the reference list. Please provide the respective references in the list or delete these citations.	